













09 April 2007

## FIELD SURVEY DRAWING ANNOTATION

Exterior Conditions Legend – Masonry



### MASONRY CONDITIONS and GRAPHIC KEY

Abbreviation	Graphic Designation	Condition	Description
DP		Displacement	Structural condition, possibly related to the deterioration of hidden steel structural elements and subsequent expansion and contraction.
ER		Erosion	Wearing away of the surface edges, corners or carved details of masonry, usually due to severe weathering, but also salts or abrasive cleaning
DL		Delamination	Delamination of strata in sedimentary stone, resulting in loss of most or all of face of stone.
CR		Cracking	Cracks through the full stone block, brick unit, or terra cotta piece. 1/16" to 1/2" wide within the masonry unit, due to stresses or flawed masonry units.
SP		Spalling	Surface pocked or flaking parallel to stone face. Could also be from mechanical damage resulting in surface stone loss.
AP		Anchors or Plugs	Miscellaneous attachments into unit face or into mortar joints.
JD		Mortar Joints - Deteriorated	Open, eroded or missing mortar joints that compromise the structural integrity or weather-tightness of the surrounding masonry.
JN		Mortar Joints - Nonmatching	Non-historic mortar joints that do not match the original mortar due to incompatible appearance (color, composition, tooling, etc.).
JS		Mortar Joints - Joint Sealants	Mortar joints that have been inappropriately repointed with sealants.
SD		Stains (Deposits)	Surface staining; identify source. Includes efflorescence or white scum, rust or copper stains, or carbonaceous deposits.
SO		Stains (Organic)	Algae or mold growth on masonry surface due to the presence of water.
RS		Replacement Material	Full or partial units, previously and recently replaced.

QUINN EVANS | ARCHITECTS

219 1/2 N. Main Street

Ann Arbor, Michigan 48104

v 734 663 5888

f 734 663 5044

www.quinnevans.com